



RENIA - Primer for PUR

Technical Data Sheet 570.000-0814

BASIS:

Clear liquid primer based on isocyanates for reinforcing aged PUR soles to allow bonding them with CR-based adhesives.

INSTRUCTIONS:

Shoe materials made of PUR-foam are likely to undergo a rapid ageing caused by microbes and water. Multi-purpose cements only bond the surface of the PUR-materials. Under heavy load or stress the spongy material will then break. Therefore the PUR bottom has to be reinforced by either coating with the vinyl-cement Renia –Syntic =TOTAL= or by **Renia – Primer for PUR**. The advantage of using Renia – Primer for PUR is its very short open time. After priming, any Renia CR–adhesive can be applied instantly.

PRETREATMENT:

Wet shoes have to be dried first by pressing the sanded shoe bottom with absorbent paper for a few seconds. repeat until the paper stays dry.

POT-LIFE:

Not applicable.

OPEN ASSEMBLY TIME:

A few seconds.

PRESSURE:

See Technical Data Sheet of the corresponding adhesive.

PROPERTIES:

Renia – Primer for PUR is sensitive to moisture and dirt. Only use a clean and dry brush. The decomposed active substance appears as a white precipitate on the bottom. Avoid working directly from the bottle to avoid contamination with PUR dust, use from a separate container instead.

SHELF-LIFE:

Six months. Store in a cool and dry place.

THINNER:

Not usable.

CLEANING:

Let the brush dry and remove remnants. Residue cannot be used any more.

LABELLING:

Hazard class	:	3	Packing Group	:	II
Code	:	Flammable liquid, nos (Ethylacetate)			
HMIS	:	1/4/1/C	UN	:	1993
NFPA	:	1/4/0/			

PACKAGES:

Article	Size	Net-Content	Unit per box
570764	3.3 fl oz - bottles	12x 3.3 fl oz	10 boxes
570765	8.5 fl oz - bottles	6x 8.5 fl oz	5 boxes